

WET RUBBING FASTNESS IMPROVER JV-528

I. PRODUCT PROFILE

The active, vulcanized, direct and indigo dyes are particularly low when they are dyed thick and dark on cellulose fibers, especially in the case of large black, red and green blue, which are often lower than grade 1, while the textile products exported to Europe and the United States require more than grade 3 to improve the stability of the products to salt and alkali and to reduce the shortage of the structure of the products themselves. Therefore, the environmentally friendly wet rubbing fastness agent has been specially developed.

II. MAIN COMPONENTS

Special Waterborne Polyurethane

III. TECHNICAL INDICATORS

Appearance: light yellow to yellow transparent liquid

Ionic: weak cation

PH value: 3.5 ± 0.5 (50g / L)

Solubility: easily dispersed in any proportion of tap water

IV. MAIN PERFORMANCE

1. This product does not contain formaldehyde and APEO. It belongs to environmental protection product and meets the requirements of EU Oeko-Tex Standard 100;
2. It can be used for fixing after dyeing cellulose fiber; it can greatly improve the wet friction effect, which can be increased by 1-1.5 grade, reaching more than 3 grade;
3. It is easy to use, and it can be used directly with water;
4. The handle of the fabric is soft, and has no effect on the color light and sunlight fastness;
5. For jeans washing is more prominent.

V. APPLICATION METHODS

According to the type and concentration of dyes used and the types and forms of treated fabrics, the usage is as follows:

1. Impregnation method (limited to water treatment plant)

Dosage: jv-528: 2-4% (o.w.f.)

Bath ratio: 1:10 ~ 20

Process: dyed fabric ($\text{pH} \leq 7$) → dipping (room temperature, time: 20 ~ 30min) → drying

2. Dip rolling process dosage: jv-528:30-50g / L;

Process: dyed fabric ($\text{pH} \leq 7$) → dip and roll (rolling yield: 80 ~ 85%) → drying

VI. POINTS FOR ATTENTION

1. Please use it immediately after preparation, and do a good job of sample test before use. The above process is only for reference.
2. The wet rubbing fastness improver jv-528 can only be used alone, and cannot be used in the same bath with silicone oil, softener, fixing agent and anionic additive.
3. The temperature of working fluid should be controlled between 25 °C and room temperature.
4. Before using the wet rubbing fastness improver jv-528, clean the cloth surface alkali (control pH ≤ 7), salt and soaping agent.
5. use a long time to produce a large amount of foam in the rolling tank. Clear the foam or clean the groove and replace the working fluid in time.
6. Try to keep the pH value of working fluid in the range of 5-6.
7. The water used for working fluid should be tap water ≤ 100 ppm.

VII. PACKAGING STORAGE

125kg / plastic barrel, sealed at room temperature, shelf life of 6 months.

东莞市洁威实业有限公司
DONGGUAN JERVAY INDUSTRIAL CO.,LTD.

Web:www.jervay.com

Contact person:Mr.Finn

Email:jv@jervay.com

Tel:+86 150 1475 1722

The above information and data are for reference only. Customers should do laboratory samples in advance to determine the specific process and dosage. The company only to product specifications, quality consistency to guarantee. Customers due to the addition of other additives, or due to process and fabric losses, the company is not responsible.